

- Tiles and sheets in different thicknesses
- Classical design in refreshed colours
- Tough and durable
- PUR surface treatment for low maintenance



STANDARD PLUS

Dark Beige



Dark Beige

- 21 003 482
- 21 004 482



Sand Dark

- 21 003 915



Sand Medium

- 21 003 914




Light Warm Grey

- 21 003 910



Sand

- 21 003 913
- 21 005 913
- 21 006 913



Sand Light

- 21 003 912
- 21 004 912



Light Grey

- 21 003 497
- 21 004 497



Stone Grey

- 21 003 924
- 21 005 924
- 21 006 924



Medium Warm Grey

- 21 003 911
- 21 004 911
- 21 005 911
- 21 006 911



Grey

- 21 003 498
- 21 004 498
- 21 005 498
- 21 006 498



Brown Grey


- 21 003 496


















Dark Stone

- 21 003 499

TECHNICAL DATA

	Standards	Standard Plus 2.0 mm	Standard Plus 1.5 mm
Classification			
Classification	ISO 10581 commercial industrial	Classes: 34 43	Classes: 32 41
Characteristics			
Total thickness	ISO 24346 (EN 428)	2.00 mm	1.5 mm
Wear layer thickness	ISO 24340 (EN 429)	2.00 mm	1.5 mm
Total weight	ISO 23997 (EN 430)	3 300 g/m ²	2 475 g/m ²
Surface treatment	-	PUR	PUR
Binder content	ISO 10581	Type II	Type II
Technical performance			
Residual indentation	Best measured value	0.04 mm	0.04 mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10 mm	≤ 0.10 mm
Reaction to fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	B _{fl} s1 ≥ 8 kW/m ² Pass	B _{fl} s1 ≥ 8 kW/m ² Pass
Dimensional stability	ISO 23999 (EN 434)	Rolls: ≤ 0.40% Tiles: ≤ 0.25%	Rolls: ≤ 0.40%
Castor wheel test	ISO 4918 (EN 425)	Suitable	Suitable
Marine equipment	IMO FTPC Part 5 and 2 IMO Res. A653	 0575	-
Static electrical charge	EN 1815	< 2 kV	< 2 kV
Light fastness	EN ISO 105-B02	≥ 6	≥ 6
Chemical resistance	ISO 26987 (EN 423)	Good resistance	Good resistance
Fungi and bacteria resistance	ISO 846: Part C	Does not favour growth	Does not favour growth
Clean room test	ASTM F51/00	Class A	Class A
Slip resistance	DIN 51130 EN 13893	R9 ≥ 0.3	R9 ≥ 0.3
Thermal resistance Underfloor heating	EN 12667 / DIN 52612	0.01 m ² K/W Suitable - max. 27°C	
Form of delivery	ISO 24341 (EN 426) ISO 24342 (EN 427)	Rolls: 23 lm x 2 m Tiles: 50 x 50 cm	Rolls: 25 lm x 2 m
Colours	EN 12667 / DIN 52612	30 (rolls) 10 (tiles)	12
CE Marking			
DoP number	-	0019-0025-DoP-2013-07	0019-0045-DoP-2013-07

Surface Treatment	Logistics Information	Laying direction	Sustainability credentials
	 Available in rolls Rolls length: 23 lm (2.0 mm)  Rolls length: 25 lm (1.5 mm)   Available in tiles	  	 ≤ 10 µg/m ³ OPTIMAL INDOOR AIR QUALITY  BIOCIDES FREE  PHTHALATES FREE  RECYCLABLE  25.5% RECYCLED CONTENT  Recycled Ready  EPD®



STANDARD PLUS

Medium Blue



Light Beige

- 21 003 479
- 21 004 479
- 21 005 479
- 21 006 479



Light Yellow Beige

- 21 003 483
- 21 005 483
- 21 006 483



Sandstone

- 21 003 484



Yellow

- 21 003 485



Gold

- 21 003 916
- 21 004 916



Orange

- 21 003 917



Red

- 21 003 488



Purple

- 21 003 918



Royal Blue

- 21 003 920



Dark Blue

- 21 003 493
- 21 005 493
- 21 006 493

Page 568

Coordinated
accessories
offer



HOMOGENEOUS

Light Yellow Beige



Medium Blue

- 21 003 492
- 21 004 492
- 21 005 492
- 21 006 492



Lime

- 21 003 922
- 21 004 922



Dark Green

- 21 003 921
- 21 005 921
- 21 006 921



Pale Green

- 21 003 923



Light Beige Grey

- 21 003 494
- 21 004 494
- 21 005 494
- 21 006 494



Light Blue

- 21 003 919
- 21 004 919



Beige Grey

- 21 003 495
- 21 004 495



Black

- 21 003 500

Logistics Information

- Available in rolls
Rolls length: 23.1m (2.0 mm)
- Rolls length: 25.1m
(1.5 mm)

- Available in tiles