


- Versatile flooring
- Harmonious and fresh colours
- Tough and durable
- Most flexible in its category



VYLON PLUS

Warm Sand - Light Cold Grey

 Green	 Green	 Green	 Green	 Green
 21 000 583  21 007 583  21 001 583	 21 000 580  21 007 580  21 001 580	 21 000 592  21 007 592  21 001 592	 21 000 590  21 007 590  21 001 590	 21 000 591  21 007 591  21 001 591
 Warm Sand	 Warm Sand	 Warm Sand	 Warm Sand	 Warm Sand
 21 000 589  21 007 589  21 001 589	 21 000 588  21 007 588  21 001 588	 21 000 596  21 007 596  21 001 596	 21 000 585  21 007 585  21 001 585	 21 000 587  21 007 587  21 001 587
 Light Cold Grey	 Light Cold Grey	 Light Cold Grey	 Light Cold Grey	 Light Cold Grey
 21 000 582  21 007 582  21 001 582	 21 000 597  21 007 597  21 001 597	 21 000 595  21 007 595  21 001 595	 21 000 581  21 007 581  21 001 581	 21 000 594  21 007 594  21 001 594
 Dark Warm Grey	 Dark Warm Grey	 Dark Warm Grey	 Dark Warm Grey	 Dark Warm Grey
 21 000 586  21 007 586  21 001 586	 21 000 584  21 007 584  21 001 584	 21 000 593  21 007 593  21 001 593		

TECHNICAL DATA

	Standards	Vylon Plus
Classification		
Classification	ISO 10581 commercial industrial	Classes: 34 43
Characteristics		
Total thickness	ISO 24346 (EN 428)	2.00 mm
Wear layer thickness	ISO 24340 (EN 429)	2.00 mm
Total weight	ISO 23997 (EN 430)	3 700 g/m ²
Surface treatment	-	Factory pre-treated
Binder content	ISO 10581	Type II
Technical performance		
Residual indentation	Best measured value	0.04 mm
	ISO 24343-1 (EN 433) requirement	≤ 0.10 mm
Reaction to fire	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2	B ₁ s1 ≥ 8 kW/m ² Pass
Dimensional stability	ISO 23999 (EN 434)	Rolls: ≤ 0.40% Tiles: ≤ 0.25%
Castor wheel test	ISO 4918 (EN 425)	Suitable
Marine equipment	IMO FTPC Part 5 and 2 IMO Res. A653	
Static electrical charge	EN 1815	< 2 kV
Light fastness	EN ISO 105-B02	≥ 6
Chemical resistance	ISO 26987 (EN 423)	Good resistance
Fungi and bacteria resistance	ISO 846: Part C	Does not favour growth
Clean room test	ASTM F51/00	Class A
Slip resistance	DIN 51130 EN 13893	R9 ≥ 0.3
Thermal resistance Underfloor heating	EN 12667 / DIN 52612	0.01 m ² K/W Suitable - max. 27°C
Form of delivery	ISO 24341 (EN 426) ISO 24342 (EN 427)	Rolls: 20 lm x 2 m Tiles: 61 x 61 cm 30 x 30 cm
Colours	EN 12667 / DIN 52612	18
CE Marking		
DoP number	-	0019-0031-DoP-2013-07

Surface Treatment	Logistics Information	Laying direction	Sustainability credentials
Factory pre-treated	 Available in rolls Rolls length: 20 lm  Available in tiles	